

# VILLAGE

280X120 — 110,24"X47,24"



R9  
R9



Rectificado  
Rectified



Antihielo  
Frost proof



No Repetitivo  
No Repetitive



Dest. Medio(v3)  
Shade Variation: Medium



Mate  
Matt



Polivalente  
Versatile



Porcelánico  
Porcelain



VILLAGE SOFT CENDRE  
BP2812RB

## CARACTERÍSTICAS TÉCNICAS / TECHNICAL CHARACTERISTICS

| Formato<br>Size | Color<br>Colour | MOHS<br>(Dureza)<br>Strength<br>Resistance | PEI            |  | DESLIZAMIENTO<br>GLIDE |             |             | Absorción<br>de Agua<br>Water<br>Absorption | Resistencia Química / Chemical Resistance |   |  |                                 |   |  |   |   | Resistencia a las<br>Manchas<br>Stain Resistance |   |  | Resistencia<br>Mecánica<br>Mechanical<br>Resistance                   |   |   |  |
|-----------------|-----------------|--|----------------|--|------------------------|-------------|-------------|---|---|---|--|---------------------------------|---|--|---|---|--|---|--|---|---|---|--|
|                 |                 |  | Clase<br>Class | Etapa<br>Abrasión<br>Abrasion<br>Stage | UNE-ENV<br>12633:2003  | DIN 51130** | DIN 51097** |   | P.D.<br>Limpieza<br>Cleaning              | Aditivos<br>Agua<br>Piscina<br>Additive<br>pools<br>water | Ácidos y Alcalis<br>Acids and Alkalis<br>(Baja concentración)<br>(Low concentration) |                                 |   |  | Ácidos y Alcalis<br>Acids and Alkalis<br>(Alta concentración)<br>(High concentration) |   |  |   | Con<br>Acción<br>Trazante<br>Tracing<br>Action | Con<br>Acción<br>Química<br>Oxidante<br>Chemical<br>Oxidize<br>Action | Con<br>Acción<br>Filmic<br>Filmic<br>Action | Resistencia<br>a la helada<br>Frost<br>Resistance | Resistencia a<br>la flexión<br>Bending<br>Resistance |
|                 |                 |  |                |  |                        |             |             |   |   |   | Ácido<br>Clorid.<br>Hydrochloric<br>Acid   | Ácido<br>Cítrico<br>Citric Acid | Hidróxido<br>Potásico<br>Potassium<br>Hydroxide | Ácido<br>Clorid.<br>Hydrochloric<br>Acid | Ácido<br>Láctico<br>Lactic<br>Acid  | Hidróxido<br>Potásico<br>Potassium<br>Hydroxide |  |   |  |   |   |   |  |
| 280X120         | Cendre          | 5  | 4              | 2100                                   | 1                      | R9          |             | <0,5%                                       | GA  | GA  | GLA  | GLA                             | GLA   | GHA                                      |   | GHA   | 5  | 5 | 5  | RESISTE   | >35N/mm <sup>2</sup>                        |   |  |



Se aconseja uso del Sistema Nivelado  
We recommend using Levelling System to fix the tiles

Fecha: 07/05/2026

BALDOCER